



Technical Data Sheet

DOWSIL™ EA-9187LH Conformal Coating

One part, medium viscosity conformal coating, UL approved.

Features & Benefits

- Solventless
- Room temperature cure with optional heat acceleration
- UV indicator
- UL 746E qualified
- Polydimethylsiloxane coating

Applications

DOWSIL™ EA-9187LH Conformal Coating is a solventless, elastomeric coating suitable for lighting, industrial and automotive industries for rigid and flexible printed circuit board (PCB), sensitive components and fine pitched designs.

Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

Property	Unit	Result
One or Two-part		One
Appearance		Clear
Viscosity	mPa-Sec	442
Skin Over Time @ 25°C	minutes	7
Specific Gravity (uncure)		0.98
NVC (Non Volatile Content)	%	97
Durometer Shore A		21
Tensile Strength	MPa	0.25
Elongation	%	100
Unprimed Lap Shear (AL)	MPa	0.24
Dielectric Strength	kV/mm	16.61
Volume Resistivity	Ohm*cm	1.62E+15

Typical Properties (Cont.)

Property	Unit	Result
Dielectric Constant @ 100 Hz		1.76
Dissipation Factor @ 100 Hz		0.02
Dielectric Constant @ 100 kHz		1.73
Dissipation Factor @ 100 kHz		0.001
UL Flammability Classification		94 V-0
Agency Listing		UL 746E

Description	<p>Solventless RTV elastomeric conformal coatings require atmospheric moisture to cure, needing no expensive ovens, and various viscosity versions facilitate different application methods. This family of coatings is rapidly gaining popularity due to its solventless formulations, its rapid cure rates that can be dramatically accelerated by mild heat, and its cost effectiveness. These elastomers, when cured, offer the optimum stress relief for even the most delicate components and interconnections in a variety of service environments. This product line also features coatings manufactured for controlled volatility and many of these products are UL recognized. Conformal coatings are materials applied in thin layers onto printed circuits or other substrates.</p>
Application Methods	<ul style="list-style-type: none"> • Spray • Brush • Flow • Automated pattern coating • May be dip coated with special precautions
Processing/ Curing	<p>Time to cure is dependent on several variables including the method of application, film thickness, temperature and humidity. Skin over time in the data table gives an indication of typical times to form a non-tacky surface. Cure time for full cure are indications of time needed to develop full physical properties such as durometer, tensile strength or adhesion. These times, including full cure time, can be significantly improved by introducing mild heat of 60°C or less.</p>
Pot Life And Cure Rate	<p>The pot life of Dow RTV conformal coatings is dependent on the application method chosen. To extend pot life, minimize exposure to ambient moisture by using dry air or dry nitrogen blanketing whenever possible.</p>
Adhesion	<p>With RTV cure coatings, adhesion typically lags behind cure and may take up to 72 hours at room temperature to build in some coatings. Dow conformal coatings are formulated to provide adhesion to most common substrates and materials. It is recommended that the coatings be applied to clean and dry substrates prior to application. Due to the vast variety of substrates used appropriate adhesion testing should be performed to insure the adhesion of the coating is adequate for the end use and should only be tested after 72 hours at room temperature. On certain difficult, low-surface energy surfaces, adhesion may be improved by priming or by special surface treatment such as chemical or plasma etching.</p>

Useful
Temperature
Ranges

For most uses, silicone adhesives should be operational over a temperature range of -45 to 200°C (-49 to 392°F) for long periods of time. However, at both the low and high temperature ends of the spectrum, behavior of the materials and performance in particular applications can become more complex and require additional considerations. For low-temperature performance, thermal cycling to conditions such as -55°C (-67°F) may be possible, but performance should be verified for your parts or assemblies. Factors that may influence performance are configuration and stress sensitivity of components, cooling rates and hold times, and prior temperature history. At the high-temperature end, the durability of the cured silicone elastomer is time and temperature dependent. As expected, the higher the temperature, the shorter the time the material will remain useable.

Repairability

In the manufacture of PCB system assemblies, it is often desirable to salvage or reclaim damaged or defective units. Dow RTV conformal coatings offer excellent reparability because they can be removed from substrates and circuitry by scraping or cutting, or by using solvents or stripping agents. If only one circuit component is to be replaced, a soldering iron may be applied directly through the coating to remove the component. Proper ventilation of any fumes should be employed. After the circuit board has been repaired, the area should be cleaned by brushing or by using solvent, then dried and recoated. Heat cure coatings can be repaired with RTV coatings, but heat cure coatings may not work well when used to repair RTV coatings.

Handling
Precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT CONSUMER.DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

Usable Life and
Storage

Special precautions must be taken to prevent moisture from contacting Dow RTV conformal coatings. Containers should be kept tightly closed and head or air space minimized. Partially filled containers should be purged with dry air or other gases, such as nitrogen. The product should be stored in its original packaging with the cover tightly attached to avoid any contamination. Store in accordance with any special instructions listed on the product label. The product should be used by its Use Before date as indicated on the product label.

Packaging
Information

Multiple packaging sizes are available for this product.

Limitations

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

Health And Environmental Information

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, consumer.dow.com or consult your local Dow representative.

How Can We Help You Today?

Tell us about your performance, design and manufacturing challenges. Let us put our silicon-based materials expertise, application knowledge and processing experience to work for you.

For more information about our materials and capabilities, visit www.consumer.dow.com.

To discuss how we could work together to meet your specific needs, go to www.consumer.dow.com for a contact close to your location. Dow has customer service teams, science and technology centers, application support teams, sales offices and manufacturing sites around the globe.

www.consumer.dow.com

consumer.dow.com

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DOW SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

